

**Clay -Howells
2011 Drill Composite
Highlites**

								Light Rare Earth Oxides				
DDH ID	From (m)	To (m)	Interval (m)	TREO %	Fe2O3(T) %	HREO%	Nb2O5%	La2O3%	Ce2O3%	Pr2O3%	Nd2O3%	Sm2O3%
CH-11-02	269.00	295.90	26.9	0.12	51.55	6%	0.07	0.0264361	0.055224	0.0060798	0.0209871	0.0027401
CH-11-06	82.5	89.4	6.9	0.57	18.33	11%	0.15	0.121941	0.2528851	0.0258723	0.0927223	0.014621
CH-11-08	57.2	73	15.8	0.67	48.41	2%	0.05	0.2074547	0.3305777	0.0289545	0.0841904	0.0069567
	and 94.17	117.65	23.48	0.46	33.48	4%	0.054	0.1409958	0.2198054	0.0194045	0.0587404	0.006013

				Heavy Rare Earth Oxides									
DDH ID	From (m)	To (m)	Interval (m)	Eu2O3%	Gd2O3%	Tb2O3%	Dy2O3%	Ho2O3%	Er2O3%	Tm2O3%	Yb2O3%	Lu2O3%	Y2O3%
CH-11-02	269.00	295.90	26.9	0.000624	0.0015705232	0.000185486	0.0008662	0.0001484	0.0003783	4.94E-005	0.0002896	4.29E-005	0.0034551
CH-11-06	82.5	89.4	6.9	0.0029199	0.0097353304	0.001328154	0.0068181	0.0012481	0.0034042	0.0004824	0.0028589	0.0004341	0.0346823
CH-11-08	57.2	73	15.8	0.0014631	0.0031000375	0.000320022	0.0015204	0.0002589	0.0006619	8.07E-005	0.0004319	5.83E-005	0.0070213
	and 94.17	117.65	23.48	0.0013854	0.0029012633	0.000304407	0.0015596	0.0002786	0.0007441	9.78E-005	0.0005673	8.04E-005	0.0083511