

TREO% Cut-off	Tonnes (x 000)	La ₂ O ₃	Ce ₂ O ₃	Pr ₂ O ₃	Nd ₂ O ₃	Sm ₂ O ₃	Eu ₂ O ₃	Gd ₂ O ₃	Tb ₂ O ₃	Dy ₂ O ₃	Ho ₂ O ₃	Er ₂ O ₃	Tm ₂ O ₃	Yb ₂ O ₃	Lu ₂ O ₃	Y ₂ O ₃	TREO
0.9%	690	0.292	0.455	0.044	0.148	0.022	0.005	0.015	0.004	0.009	0.002	0.005	0.001	0.004	0.001	0.051	1.058
0.8%	1,612	0.251	0.403	0.039	0.133	0.020	0.005	0.014	0.005	0.009	0.002	0.004	0.001	0.003	0.000	0.045	0.934
0.7%	4,293	0.210	0.353	0.035	0.119	0.018	0.005	0.012	0.005	0.008	0.001	0.004	0.000	0.003	0.000	0.041	0.816
0.6%	8,477	0.183	0.318	0.032	0.110	0.017	0.004	0.011	0.004	0.007	0.001	0.003	0.000	0.003	0.000	0.036	0.732
0.5%	15,293	0.159	0.282	0.029	0.099	0.015	0.004	0.010	0.004	0.006	0.001	0.003	0.000	0.002	0.000	0.033	0.649
0.4%	25,059	0.138	0.248	0.025	0.088	0.014	0.004	0.009	0.003	0.006	0.001	0.003	0.000	0.002	0.000	0.030	0.571
0.3%	35,496	0.121	0.219	0.023	0.079	0.012	0.003	0.008	0.003	0.005	0.001	0.002	0.000	0.002	0.000	0.027	0.507
0.2%	40,422	0.114	0.205	0.021	0.075	0.012	0.003	0.008	0.003	0.005	0.001	0.002	0.000	0.002	0.000	0.025	0.476